

DERWENT-ACC-NO: 1982-08281J

DERWENT-WEEK: 198250

COPYRIGHT 2006 DERWENT INFORMATION LTD

TITLE: Ornamental sintered nickel alloy -
contains aluminium and has gold colour with good wear
and corrosion resistance

PATENT-ASSIGNEE: MITSUBISHI METAL CORP[MITV]

PRIORITY-DATA: 1981JP-0064095 (April 30, 1981)

PATENT-FAMILY:

PUB-NO	PAGES	PUB-DATE	
LANGUAGE		MAIN-IPC	
JP 57181354 A		November 8, 1982	N/A
003	N/A		
JP 85047889 B		October 24, 1985	N/A
000	N/A		

APPLICATION-DATA:

PUB-NO	APPL-DESCRIPTOR	APPL-NO
APPL-DATE		
JP 57181354A	N/A	1981JP-
0064095	April 30, 1981	

INT-CL (IPC): C22C001/05, C22C019/03

ABSTRACTED-PUB-NO: JP 57181354A

BASIC-ABSTRACT:

Light and hard ornamental Ni-Al sintered alloy having golden colour tone and excellent in wear as well as corrosion resistance, consists of Al 24-30 wt.% and the balance Ni with incidental impurities.

The alloy is provided with density 6.08-6.36 g/cm³, Vicker's hardness 520-640, deflective strength 115-135 kg/mm² and presents light golden colour. A

commercially available Ni-Al alloy powder of Al 32-33%, may be mixed with a desired amount of Ni powder, sintered 1,300-1,550 deg.C in a reducing, inert gas or vacuum atmosphere, and if required subjected to hot hydrostatic pressure.

TITLE-TERMS: ORNAMENT SINTER NICKEL ALLOY CONTAIN ALUMINIUM
GOLD COLOUR WEAR
CORROSION RESISTANCE

DERWENT-CLASS: M22

CPI-CODES: M26-A02; M26-B08; M26-B08A;